CAMEX LIMITED
REGD. OFF.: CAMEX HOUSE, 2ND FLOOR, STADIUM - COMMERCE ROAD, NAVRANGPURA, AHMEDABAD - 380 009
PH.: 66307200, 26462260, 26462262 FAX: 91-079-26462123
WEB: camexcolours.com E-MAIL: camex@icenet.net

CAMAMICRO CLN

BINDER FOR PIGMENT PRINTING

SALIENT FEATURES

- ► Forms film with good elasticity, transparent & soft
- ► Excellent re-emulsification properties
- ► Enables to produce sharp & brighter prints
- ► High resistance to mechanical shear
- ► Excellent thermal stability

CHARACTERISTICS

Appearance	: Milky white liquid
Chemical Nature	: Co-polymeric compound
Ionic Nature	: Nonionic
Miscibility	: Easily miscible with water in all proportions
pH	: 7.5 ± 0.5
Compatibility	: Excellent with Thickeners & Pigment Emulsions

APPLICATION

Substrate	: Cellulosic fabric & its blends with polyester
Machines	: Printing equipments & machines
Function	: Binder in pigment printing
Guide Recipes	:

- ***Preparation of Stock Paste-***

CAMAMICRO CLN	**10 – 20 parts**
CAMATHICK CME	**1.5 – 1.7 parts**
Printosoft	**0.5 – 2.0 parts**
Water	**To bulk up to 100 parts**

If required, add ammonia (up to 0.75%) to keep ph 8.5 – 9

- ***Preparation of Print Paste-***

Pigment Emulsion	**x parts**
CAMAFIX CCL (add just before printing)	**1 part**
Stock paste	**To bulk up to 100 parts**

- Print – Dry – Cure at 150° C for about 4 minutes.

SPECIAL REMARKS

Storage Stability	: Minimum 6 months under normal conditions of storage
Container	: 50 & 200 kg Carbuoys & barrels

Disclaimer: All recommendations for the use of our products, whether given by us in writing, orally or to be implied from the results of trials, are based on our present state of knowledge & experience. Owing to the variation in local application conditions, they can not be claimed to be complete. Hence, we can not accept any responsibility thereof. All claims, liabilities – also with a view to claim of third parties – are excluded. It is advised to conduct lab & bulk trials before using in bulk production.