CAMEX LIMITED
REGD. OFF. : CAMEX HOUSE, 2ND FLOOR, STADIUM - COMMERCE ROAD, NAVRANGPURA, AHMEDABAD - 380 009
PH. : 66307200, 26462260, 26462262 FAX : 91-079-26462123
WEB : camexcolours.com E-MAIL : camex@dataone.in

CAMOL NFSN

HIGH PERFORMANCE WASHING – OFF CHEMICAL

SALIENT FEATURES

- ► High complexing property with protective colloid
- ► Low foaming in circulatory liquor machines
- ► Suitable in pretreatment, dyeing & washing – off baths
- ► Prevents bleeding in silicate fixation of reactive dyes
- ► Prevents interference of heavy metal ions in wet processes
- ► Prevents redeposition of foreign particles
- ► Enables better removal of silicate & gum from prints in washing
- ► Enhances fastness, brightness & luster of dyed substrate
- ► Prevents oligomer deposition in disperse dyeing

CHARACTERISTICS

Appearance : Viscous, clear liquid
Chemical Nature : Synergetic blend of dispersants, chelates & protective colloid
Ionic Nature : Nonionic
Solubility : Easily miscible with water in all proportions at room temperature
pH (1% aq. Sol.) : 7 to 8
Stability : Stable to alkalis, acids, electrolytes and reducing agents in the concentrations normally used in practice. Stable to oxidizing agents except persulphate & chlorine

APPLICATION

Substrate : Cellulosic, synthetic textiles
Machines : All kinds of processing machines
Function : Multipurpose chemical in all wet processes
Guide Recipes : Add after dilution with water or directly to the bath.

- 1.0 – 1.5 g/l in pretreatment bath
- 1.0 – 1.5 g/l in dyeing bath before addition of dyestuff
- 0.5 – 1.0 g/l in washing – off of reactive dyed / printed material
- 0.5 – 1.0 g/l in silicate pad bath for Pad – batch method

SPECIAL REMARKS

Storage Stability : Minimum 6 months under normal conditions of storage
Container : 50 & 200 kg Carbuoys & barrels

Disclaimer: All recommendations for the use of our products, whether given by us in writing, orally or to be implied from the results of trials, are based on our present state of knowledge & experience. Owing to the variation in local application conditions, they can not be claimed to be complete. Hence, we can not accept any responsibility thereof. All claims, liabilities – also with a view to claim of third parties – are excluded. It is advised to conduct lab & bulk trials before using in bulk production.