




Solvent Red 119

Technical Data Sheet



Product Name : **Solvent Red 119**

■ **PHYSIO - CHEMICAL PROPERTIES** (Rating 8 represents Highest fastness & 1 represents Lowest fastness)

Light Fastness	:	3 (Nitro Cellulose Printed Wet film 6 Micron)
	:	3 (Thermosetting Acrylic Printed Wet film 24 Micron)
Melting Point	:	115°C
Thermal Resistance	:	300°C
pH (1% Solution)	:	6 - 7
Bulk Density (Lit./Kg.)	:	2.5 - 3.0
Specific Gravity	:	1.8993

■ **SOLUBILITY** (Unit: Gm/lit (At Room Temp.); TR: Trace)

Methyl Ethyl Ketone (MEK)	:	100
Methyl ISO Butyl Ketone (MIBK)	:	75
Acetone	:	150
Ethyl Acetate	:	10
Diacetone Alcohol	:	50
Butyl Cellosolve	:	100
Ethyl Cellosolve	:	100
Ethanol	:	10
Methoxy Propanol	:	200
Toluene	:	TR

■ **RESISTANCE TO CHEMICAL & FOOD STUFFS** (Rating 5 represents Highest Fastness & 1 represents Lowest Fastness)

Caustic Soda	:	5
Acetic Acid	:	4
Lactic Acid	:	5
Butter/Margarine	:	3
Paraffine Wax	:	5
Soap	:	3
Water (80 °C, 30 Min.)	:	5
Water (Boil, 30 Min.)	:	5
Coconut Oil	:	5
Cheese	:	4

■ **PRODUCT APPLICATIONS**

Suitable for Plastics, Printing Inks, Metallised Polyester Films, Aluminum Foil Coating, Stoving enamels, Leather Coating, Wood Finishes, Packaging Industry, etc.

■ **PACKING**

25 Kgs. Corrugated Boxes



Camex
LIMITED

Camex Limited

Camex House, 2nd floor Stadium-Commerce Road, Navrangpura, Ahmedabad - 380 009, Gujarat, INDIA.

P : +91 79 6630 7300 | F : +91 79 6630 7342 | E : sales@camex.co.in